

<b>Data Sheet 6mm</b>		<b>Magply® Magnesium Oxide Board</b>	
<b>Company information</b>			
<p><u>Manufacturer:</u>          IPP Ltd          Bradwell Hall          Bradwell on Sea          Essex CM0 7HX          Tel: 0044 (0)1621 776252, Fax: 0044 (0)1621 776688</p>			
<b>Board Sizes &amp; Weights</b>			
<u>Board Size</u>		<u>Weight per board (6.6 kg/m<sup>2</sup>)</u>	
1200mm x 800mm (0.96m <sup>2</sup> )		6kg	
1200mm x 2400mm (2.88m <sup>2</sup> )		19kg	
<b>Thermal Properties</b>			
Thermal Conductivity ( $\lambda$ )		0.19 W/mK	
Thermal Resistance (R)		0.032 m <sup>2</sup> K/W	
<b>Fire Performance</b>			
BS EN 476 (Parts 6&7)		Class 0	
Euroclass EN13501		A1 (Non-Combustible)	
<b>Physical &amp; Chemical Properties</b>			
<u>Appearance:</u>	Solid flat sheet board	<u>Colour</u>	White
<u>Odour:</u>	Odourless	<u>Change of State:</u>	None
<u>Melting point:</u>	2400°C	<u>Ignitability:</u>	N/A
<u>Spontaneous ignition:</u>	N/A	<u>Explosion hazard:</u>	N/A
<u>Oxidising properties:</u>	N/A	<u>Vapour pressure:</u>	N/A
<u>Density</u>	1100 g/m <sup>3</sup>	<u>pH level:</u>	7.5
<u>Solubility:</u>	Insoluble in Water		
<b>Stability and Reactivity</b>			
<u>Special physical conditions to be avoided</u> None			
<u>Incompatible Materials</u> Not known			
<u>Hazardous Decomposition Products</u> None			
<u>Reaction to Frost</u> Magply is freeze/thaw resistant			
<u>Reaction to Moisture</u> Magply is breathable and water-resistant. Passage of moisture does not affect its structure			
<u>Reaction to Insects/Rodents</u> Magply is inert and has no nutritional value, rendering it unattractive to insects and rodents.			

**Fixings, Sealants, Adhesives**

It is considered good practice that stainless steel fixings are used with Magply and screws should have a thread the whole length of the shank (to the tip) for maximum strength and resistance. Specialist details are available.

The length of fixings depends on national regulations and applications. As a guide, the fixing should be a minimum of 28mm plus the thickness of the board

For standard drywall applications, a minimum 12 $\mu$  galvanised or phosphate coated fixing along with standard jointing and taping. For fire resistant applications, an intumescent sealant should be used.

Magply must be prepared with a nano-particle acrylic dispersion before plastering, rendering, wallpapering and painting if required. PVA primers are not recommended.

**Cutting**

Magply is easily cut to size using the score and snap method using a utility knife. Mark the area out with a pencil and straight edge ensuring the reinforcing mesh is cut through. Mechanical cutting is also possible; please see Magply COSHH sheet for more details.

**Liability**

The information given is correct to the best of our knowledge at the time of publication but without guarantee of accuracy. We do not accept any responsibility for damage and claims arising from handling, transport, storage or disposal of the product. This data sheet applies only to the product named above supplied by IPP. If the product is used as part of other products, information given in the data sheet may be invalidated. E&OE

No warranty is hereby expressed or implied.

**IPP Black Mountain**

Bradwell Hall, Bradwell on Sea, Essex CM0 7HX  
Tel: 01621 776252 Fax: 01621 776688